

# vitality style | LAMINATED WOODEN FLOORINGS



STY-381(AP) BARN OAK

# SOL<sup>TM</sup>

From The World's Leading  
Flooring Manufacturer  **UNILIN**

## WATER PROOF LAMINATE FLOORING SERIES



**UNICLIC** <sup>®</sup>  
Patented Technology

<sup>®</sup>  
Inspire Decor Space



# vitalitystyle



STY-575(AP) VICTORIAN BROWN OAK

## Features:

- ◆ Water-Proof Series
- ◆ 4V Groove
- ◆ True-to-Nature Texture
- ◆ AC4, Class 32 Durability
- ◆ Uniclic Installation System
- ◆ 25-Year Residential Warranty
- ◆ 5-Year Wet Warranty
- ◆ 10-Year Commercial Warranty





# SOL<sup>TM</sup>

From The World's Leading  
Flooring Manufacturer



## vitalitystyle



### STY-174(AP) HONEY OAK

Standard Planks: 1261 x 192mm (49.6" x 7.5")

4V Groove

### STY-175(AP) BRANDON OAK

Standard Planks: 1261 x 192mm (49.6" x 7.5")

4V Groove



Inspire Decor Space



## UNILIN

FOR SMART LIVING





**STY-177(AP) FROZEN OAK**  
Standard Planks: 1261 x 192mm (49.6" x 7.5")  
4V Groove

**STY-178(AP) REFINED MODERN OAK**  
Standard Planks: 1261 x 192mm (49.6" x 7.5")  
4V Groove







STY-381(AP) BARN OAK

Standard Planks: 1261 x 192mm (49.6" x 7.5")  
4V Groove





# SOL<sup>TM</sup>

From The World's Leading  
Flooring Manufacturer



## vitalitystyle



### STY-418(AP) NATURAL BIEGE OAK

Standard Planks: 1261 x 192mm (49.6" x 7.5")

4V Groove

### STY-575(AP) VICTORIAN BROWN OAK

Standard Planks: 1261 x 192mm (49.6" x 7.5")

4V Groove



Inspire Decor Space



FOR SMART LIVING





# STY-178(AP) REFINED MODERN OAK

## vitalitystyle

### TECHNICAL SPECIFICATION

#### DIMENSIONS

FORMAT	
Length	1261 mm
Width	192mm
Number of panels per pack	9
m² per pack	2.1790
Bevels	4/lacquered
Thickness	8 mm
Tongue and groove	Uniclic
Water resistant	Yes

#### FACTORY WARRANTY

	METHOD	PARAMETERS	VALUES
Usage class	EN 13329		Class
CE	EN 14041:2004 / AC:2006	Notified body	NB 0766 - EPH Dresden
UKCA	EN 14041:2004 / AC:2006	Approved body	AB 0321 - Satra UK
	Residential use	See warranty conditions	
Warranty	Commercial use	See warranty conditions	
	Water resistency	See warranty conditions	

#### GENERAL DATA (ACCORDING TO EN 13329)

	METHOD	PARAMETERS	NORM REQUIREMENTS	VALUES
Wear resistance	EN 13329		≥ 4000 cycles	≥ 4000 cycles
Wear class	EN 13329		AC4	AC4
Impact resistance	EN 17368d	Small ball	≥ 35mm	≥ 35mm
	EN 13329	Big ball	≥ 750mm	≥ 750mm
Scratch resistance	EN 438-2, 25		Charge ≥ 3N	Charge ≥ 3N
Effect of a castor chair	ISO 4918 (with underlay)	Type W (EN 12529)	25000 cycles	No change
Thickness swelling	ISO 24336	After 24h immersion at 20°	≤ 18%	≤ 18%
Locking strength	ISO 24334	F10,2 long side	≥ 1 kN/m	≥ 1 kN/m
		Fmax long side		≥ 1 kN/m
		Fs0,2 short side	≥ 2 kN/m	≥ 2 kN/m
		Fmax short side		≥ 2 kN/m
Effect of a furniture leg	EN 424		No damage shall be visible, when tested with foot type 0	No visible damage
Resistance to staining	EN 438	Group 1,2	Class 5	Class 5
Light fastness	EN ISO 4892 2:2006/A1:2009 Procedure B - Cycle 5	Group 3	Class 4	Class 4
		Grey reference	Class ≥ 4	Class 4

#### ENVIRONMENT, SAFETY & HEALTH

	METHOD	PARAMETERS	NORM REQUIREMENTS	VALUES
Formaldehyde emission	EN 717-1	ppm	E1 < 0,1	< 0,01
Anti-static	EN 1815		≤ 2,0 kV	≤ 2,0 kV
Reaction to fire	EN 13501-1	Class		Cfl-s1
Thermal resistance	EN 12996:2001	m²K/W		0,055 m²K/W
Slip resistance	EN 13893	μ	μ ≥ 0,30	DS: μ ≥ 0,30







STY-581(AP) BARN OAK

STY-174(AP) HONEY OAK

SOL<sup>TM</sup>

From The World's Leading  
Flooring Manufacturer  UNILIN

vitality style



SCAN TO DOWNLOAD CATALOGUE



CPS<sup>®</sup>

Inspire Decor Space

Distributed By

